



# Temafloor 200 Primer

## DESCRIPTION

A two-component solvent-free epoxy varnish.

## PRODUCT FEATURES AND RECOMMENDED USES

- Thinned Temafloor 200 Primer penetrates well into the pores of the concrete sealing the surface and giving good adhesion for coatings and screeds.
- Mixed with sand also suitable for patching of concrete floors.
- Suitable for priming of new and old concrete floors prior to applying Temafloor coatings and screeds.

## TECHNICAL DATA

### Volume solids

approx. 100%

### Specific gravity

1.1 kg / litre (mixture).

### Mixing ratio

Base	2 parts by volume	Temafloor 200 Primer
Hardener	1 part by volume	Temafloor 200 Primer Hardener

By weight

Base	2,3	parts by weight	Temafloor 200 Primer
------	-----	-----------------	----------------------

Hardener	1 part by weight	Temafloor 200 Primer Hardener
----------	------------------	-------------------------------

Note! Mixing ratio by weight was calculated base on average density of the components.

### Pot life (+23°C)

About 15 minutes after mixing, on substrate.

### Practical coverage

Coverage on concrete floors is on the average:

1st primer coat 4–8 m<sup>2</sup>/l

2nd primer coat 6–10 m<sup>2</sup>/l

Practical coverage depends on the porosity and evenness of the substrate and on the application method.

### Drying time (+23°C)

Dust dry after 3 hours

Touch dry after 5 hours

Recoat after 6–12 hours

Light trucking after 16 hours

Fully cured after 7 days

The drying times are for Temafloor 200 Primer thinned 30% with Thinner 006 1029.

### Thinners

Thinner 1029, Thinner 1031

### Cleaning of equipment

Thinner 1029, Thinner 1031

### Finish

High gloss.

### Colors

Clear

### VOC

VOC 2004/42/EC (cat A/j) 500 g/l (2010)

Temafloor 200 Primer: max. VOC < 500 g/l

### Can sizes

20,0 L, 200,0 L



# Temafloor 200 Primer

## APPLICATION INSTRUCTIONS

<b>Surface preparation</b>	Always remove all grease, oil, and other impurities with Maalipesu detergent before grinding. Remove laitance or old peeling paint layers by power grinding, milling, or vacuum grit blasting. Choose the method best suited for the premises and according to the subsequent coat. Clean out pot holes removing all loose or brittle material. Open cracks with e.g. an abrasive tool. After mechanical pre-treatment remove all loose material and dust carefully with a vacuum cleaner. The substrate must have a tensile strength above 1.5 MPa. For application on cementitious leveling screed: check compatibility with the leveling screed manufacturer.
<b>Application conditions</b>	The relative humidity of the concrete should not exceed 97%. Residual moisture content of the concrete should be below 4 weight-%. The temperature of the ambient air, surface or coating should not fall below +15°C during application or drying. Relative humidity of air should not exceed 80%.
<b>Mixing components</b>	First stir base and hardener separately. Mix the correct proportions of base and hardener thoroughly (approx. 2 minutes to get homogenous mixture) by using a low speed industrial hand drill with a paddle. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface, weaken the properties of the coating and risk the success of the application.
<b>Application</b>	Roller, steel or rubber trowel.
<b>Priming</b>	Prime using 30–50% thinned Temafloor 200 Primer epoxy varnish. Pour the varnish mixture onto the floor and apply as much as is needed to impregnate the concrete surface. If necessary, repeat priming to get a non-porous surface. A porous priming coat will result in holes and air bubbles in the finished coating. Subsequent treatment can be carried out using "wet-on-wet" technique.
<b>Patching</b>	Patch pot-holes and cracks with a mixture of unthinned Temafloor 200 Primer epoxy varnish and dry, clean sand or Temafloor Thickener. Mixing ratio e.g. 1 part by volume of varnish mixture and 1–2 parts by volume of sand of grain size 0.1–0.6 mm. Make sure the patched areas are flat before priming. Sand if needed. Note! Concrete surface should always be primed before patching.
<b>Topcoating</b>	Topcoating should be done within 24 hrs after priming. If the primed surface is not topcoated within 24 hrs, it should be abraded.

<b>HEALTH AND SAFETY</b>	Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Tikkurila Oyj.
--------------------------	---

### For industrial and professional use only.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.



## Temafloor 200 Primer

# Temafloor 200 Primer

## EN 13813

The European harmonized productstandard EN 13813:2002 defines the requirements for Screed materials and floor screeds, including synthetic resin screeds.

This product is tested and CE-labelled in accordance with the tables ZA.1.5 and ZA.3.3 in the appendix ZA.3.

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 VANTAA	
11	
TIK-8400-5004b	
EN 13813 SR-B2,0	
Synthetic resin screed.	
Impact resistance	according to the top coat
Capillary absorption and permeability to water	according to the top coat
Chemical resistance	according to the top coat
Release of corrosive substances	SR
Abrasion resistance	according to the top coat
Thermal resistance	NPD
Reaction to fire	E <sub>fl</sub> 1)
Adhesion strength by pull off test	B 2,0
Release of dangerous substances	NPD
Sound absorption	NPD
Sound insulation	NPD



## Temafloor 200 Primer

1) In accordance with Commission decision 2010/85/EC

# Temafloor 200 Primer

## EN 1504-2:2004

The European harmonized productstandard EN 1504-2:2004 defines the requirements for surface protection systems for concrete.

This product is tested and CE-labelled in accordance with the tables 1d and 1f in the appendix ZA as part of coating systems.

	
0809	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
0809-CPD-0773	
TIK-8400-5004a	
EN 1504-2:2004	
Product for protection and repair of concrete structures – Coating.	
Permeability to CO2	according to the top coat
Impact resistance	according to the top coat
Capillary absorption and permeability to water	according to the top coat
Abrasion resistance	according to the top coat
Reaction to fire	E <sub>fl</sub> (NPD)
Adhesion strength by pull off test	≥ 2,0 N/mm <sup>2</sup>
Release of dangerous substances	NPD
Permeability to water vapour	according to the top coat